

1346 231

- (21) Application No. 29419/71 (22) Filed 23 June 1971
 (31) Convention Application No. P 20 32 072.3
 (32) Filed 29 June 1970 in
 (33) Germany (DT)
 (44) Complete Specification published 6 Feb. 1974
 (51) International Classification D04H 1/00 D01G 25/00//D01D 5/04
 (52) Index at acceptance

D1N 1D
 B1T 552 576 602 626 641 646 713
 B2J 1B
 B5B 350 35Y 360 365 400 409

- (72) Inventors WALTER SIMM, CLAUD GOSLING
 RICHARD BONART and BELA VON FALKAI



(54) FILTER MADE OF ELECTROSTATICALLY SPUN FIBRES

(71) We, BAYER AKTIENGESELLSCHAFT, formerly Farbenfabriken Bayer Aktiengesellschaft, a body corporate organised under the laws of Germany, of 509
 5 Leverkusen, Germany, do hereby declare the invention, for which we pray that a patent may be granted to us, and the method by which it is to be performed, to be particularly described in and by the following statement:—
 10

The invention relates to fibre filters and to a process for their production.

Processes are known by which various types of spun fibres can be processed on textile machines such as carding machines or stitching machines to produce fibre fleeces. The fibre structure of these is such that particles of dust contained in a gas flowing through the fleece are retained by the fibres, so that
 15 such fleeces may be used as air filters. The efficiency of such filters depends to a large extent on the fineness and density of the fibres. Another important influence on the filtering action is the electrostatic charge of the fibres, which produces powerful, non-homogeneous electric fields inside the fleece,
 20 by means of which charged or uncharged dust particles are deposited on the fibre surface where they are retained by adhesive forces. Charges of this kind may be produced e.g. by friction in the fibre material while it is being processed to form a fleece. It is also known to use for this purpose fibre mixtures which are made of various materials
 25 which take up different charges as the result of friction against each other so that potential differences and non-homogeneous electric fields are produced between the fibres.

The best filtering effects may be expected when very fine fibres can be combined with powerful and stable electric charges.

The conventional spinning processes provide fibre thicknesses which are generally above 10 μm . Fine fibres are required for pro-

ducing fine dust filters and "absolute filters" 45 which will efficiently retain particles of the order of less than 0.5 μm .

It is an object of the invention to develop a process by which very fine fibres can easily be produced to form a fleece in which high electrostatic charges have been generated at the production stage. 50

Accordingly the invention provides a fibre filter which comprises a gas permeable support layer and applied thereto a fibre fleece, which fleece has been produced by electrostatically spraying an organic solution of the material which is to form the fibres on to a conductive support. 55

The electrostatic spinning process comprises spraying electrostatically in known manner the fibre material from the liquid state and depositing this on a conductive support. Very thin, relatively short and highly charged fibres are obtained in large numbers. They are deposited in a uniform distribution on the conductive support where they form a complete fleece which can be lifted off when the installation has been switched off. 60

The principle of producing fibres from fibre forming liquids has been known for a long time (see e.g. German Patent No. 689,870) but the process has not reached the stage of technical application because the fibres were unsuitable for the textile industry and the electrode arrangements used for spinning could not be used in continuous operation because the technical defects were too great. 70

Fibres having thicknesses of less than 1 μm can be produced by the electrostatic process. The fibres are frequently in the form of bands and when viewed in the electron microscope they are found to have a very porous surface structure. 75

Since fleeces made of such very thin fibres are soft and liable to become damaged at least one face is protected with a support 80

85

layer which is permeable to gas. For this reason, the fibre material is preferably sprayed on to an electrode whose surface is covered with the support layer which is gas-permeable. The support layer is advantageously made of a conventionally produced fabric or fibre fleece which has a fairly coarse structure. When producing the filters in accordance with the invention, the precipitation electrode is preferably covered with this fabric and then directly sprayed electrostatically with the fine fibres.

The spinning liquids used are advantageously solutions of high polymers in readily volatile organic solvents. Suitable high polymers are, for example, polystyrene, cellulose esters or polycarbonate. The solvents used may advantageously be non-combustible liquids such as methylene chloride, chloroform, carbon tetrachloride and the like.

It will be understood that incrustations are readily formed on the electrode surface due to the rapid evaporation of the solvent. For this reason, the known form of electrodes used for lacquer spraying such as rotating bells, discs or fixed spray edges are not suitable for the spinning process because the spray process would be blocked after a short time by the dried up liquid at the spray edge.

It has been found that these disadvantages can be obviated by spraying from a rotating annular electrode. The used surface of the annular electrode is always drawn completely through the liquid bath in which the dried residues are cleaned off and the electrode is rewetted. Electrode designs of this type are already known for the production of aerosols.

It has also been found that the thickness of the fibres can be influenced by the electric conductivity of the spinning liquid. It increases with decreasing conductivity of the liquid. It has been found that fibre thicknesses which are especially suitable for producing the filters can only be spun from liquids which have an electric conductivity in the region of from $10^{-9}\text{Ohm}^{-1}\text{cm}^{-1}$ to $10^{-4}\text{Ohm}^{-1}\text{cm}^{-1}$. The conductivity can in most cases be adjusted to the required value by adding to the spinning liquid a suitable quantity of organic salts which form ions. The conductivity may also be altered by the suitable action of various solvents or of the dissolved substances.

The air temperature and relative humidity also have a marked influence on the formation of thin, dry threads. It has been found that the optimum conditions for producing good fibre fleeces are at air temperatures of between 20°C and 30°C and relative humidities of less than 40%.

The filtering action of the fibre fleeces for minute dust particles is due to a considerable extent to the action of electric fields between the fibres. To increase the field strength, it is necessary to produce higher potential gradi-

ents within the fleece. According to a further embodiment of the invention, the greatest potential differences can be obtained when the filter layer is composed of partial layers of fibres with positive and negative charges, the alternating charge on the partial layers being produced by spraying the fibre substances with spray electrodes of alternating polarity.

Owing to the low conductivity of dry, thin fibres of high polymers, the charges produced in this way are retained within the layers for several months.

The efficiency of the fibre filters can be further improved by incorporating coarse and fine fibres into the fleece, the coarse fibres providing a mechanically sturdy structure and the fine fibres advantageously providing the effective filtering component. This effect can be achieved by successively spraying different spinning solutions of higher and lower conductivity and depositing the resulting fibres on the same support.

The fibre filters produced by the process according to the invention thus consist of a fibre fleece which has been electrostatically sprayed from the liquid state on to a conductive support and which is covered with a gas permeable support layer on one or on both sides.

The spinning solutions for spraying advantageously consist of solutions of high polymers in readily volatile organic solvents.

These spinning solutions advantageously contain additives which render them conductive so that their conductivity will be in the region of from $10^{-9}\text{Ohm}^{-1}\text{cm}^{-1}$ to $10^{-4}\text{Ohm}^{-1}\text{cm}^{-1}$.

Another improvement of the fibre filters according to the invention is characterised in that the filter layer is composed of several partial layers with positive and negative charges. Fibre filters having several fibre layers superimposed on each other have also been produced. These fibre layers were sprayed from spinning solutions of different conductivities. The fibre filters produced in this way also have very advantageous properties.

The process according to the invention will now be further described with reference to the accompanying drawings. In the drawings,

Figure 1 shows an installation for the production of fibre fleeces under the action of powerful electric fields and

Figure 2 shows the annular spray electrode.

The whole installation consists in principle of a spray electrode 1 from which the spray liquid is sprayed and precipitation electrodes 2 on which the electrically charged fibres are deposited. The voltage between the electrodes is between 50 and 200 kV. The electric supply to the installation is from the high voltage source 3. The deposited fibre material 4 is carried out of the spray zone by movable electrodes, e.g. conveyor belts 5. The stripper 6 serves for the continuous removal of the

deposited fibre material. The solutions which are to be spun are contained in the storage tank 7 from which the spinning liquid is continuously removed by the annular electrode 8 and carried into the spray chamber 9 where the spinning process takes place. The solvent vapours produced are discharged through an exhaust vent 10.

Figure 2 shows the annular electrode in side view. The annular electrode 8 is rotatably mounted on rollers 11, 12 and 13 and dips with its lower part into the spinning liquid 14. The drive is provided by the insulating shaft 15 via the transmission 16 (Figure 1).

On rotation in the direction of the arrow, a thin layer of liquid on the surface of the ring is carried to the outside where it can be sprayed under the influence of the electric field. Numerous liquid points 17 which merge into thin spinning threads at their ends are formed on the exposed film. The spinning threads become detached and solidify by evaporation of the solvent. When they detach themselves, the threads are highly charged and owing to their charge they move in the electric field towards the precipitation electrode where they are deposited to form a fleece.

The following Examples illustrate the invention:—

Example 1

A spinning liquid is prepared from a 10% solution of polystyrene (molecular weight approximately 180,000) in methylene chloride. The electric conductivity of the solution is $\kappa=2.10^{-7}$ Ohm⁻¹cm⁻¹. The spray electrode is an annular electrode as shown in Figure 2 having a diameter of 1 m. The distance from the precipitation electrodes arranged on the two sides of the ring is in each case 0.5 m. There is a voltage of 120 kV between the ring and the precipitation electrodes, the ring being positive. The ring rotates at a rate of 30 revs/min during the spray process. A fleece of 2 to 3 mm in thickness of dry, porous polystyrene fibres which have different thicknesses, the average thickness being about 20 μ m, is formed after a few minutes on the precipitation electrodes which are covered with support layers which are thin highly permeable cellulose fleeces which have been produced by conventional methods. An air filter which is immediately ready for use and which is practically impermeable to dust particles in the air which have a particle diameter of more than 0.5 μ m is obtained by removing this coated support fleece from the electrodes and placing two layers together with the surfaces which are not covered by the support fleece in contact.

Example 2

A 12% solution of polycarbonate (molecular weight about 50,000 in methylene chlor-

ide) has a conductivity of $\kappa=1.10^{-3}$ Ohm⁻¹cm⁻¹. The conductivity is increased to 1.10^{-6} Ohm⁻¹cm⁻¹ by the addition of a few drops of a concentrated solution of dimethyl-tetradecylbenzylammonium bromide in methanol to 1 litre of spinning liquid. This spinning liquid is sprayed in the apparatus described in Example 1 on to support layers. A fibre filter in which the fibres have a band shaped appearance and an average thickness of 5—10 μ m is obtained. The surface of each fibre is permeated with pores of 0.1 to 0.2 μ m. The filter effect is practically complete for dust particles greater than 0.3 μ m.

Example 3

A 12% solution of polyacrylonitrile in dimethylformamide has the extremely high conductivity of 1.10^{-4} Ohm⁻¹cm⁻¹. An extremely finely fibred fleece having fibre thicknesses of about 0.4 μ m and a very efficient filter action is obtained by spraying the spinning liquid from the positive annular electrode described in Example 1 on to a support layer.

WHAT WE CLAIM IS:—

1. A fibre filter which comprises a gas permeable support layer and applied thereto a fibre fleece, which fleece has been produced by electrostatically spraying an organic solution of the material which is to form the fibres on to a conductive support.

2. A filter as claimed in Claim 1 in which the fibre fleece has been formed directly on the support layer by placing the support layer on top of the conductive support.

3. A filter as claimed in Claim 1 or Claim 2 in which the fibre fleece is provided with gas permeable support layers on both faces.

4. A filter as claimed in any of Claims 1 to 3 in which the support layer(s) is or are a fabric or a relatively coarse fibre fleece.

5. A filter as claimed in Claims 1 to 4 in which the solution used for forming the fibre fleece is a solution of high molecular polymeric material.

6. A filter as claimed in Claim 5 in which the polymeric material is a polystyrene cellulose ester or polycarbonate.

7. A filter as claimed in any of Claims 1 to 6 in which the conductivity of the solution used for spraying is 10^{-9} Ohm⁻¹ cm⁻¹ to 10^{-4} Ohm⁻¹ cm⁻¹.

8. A filter as claimed in Claim 7 in which the solution used for spraying comprises additives to render the solution more conductive.

9. A filter as claimed in any of Claims 1 to 8 in which the polarity of the spraying electrode has been alternated to provide layers of fibres in the fleece produced which are of opposite polarity.

10. A filter as claimed in any of Claims 1 to 9 in which at least two different solutions,

of differing conductivities, have been sprayed successively onto the support.

11. A filter as claimed in Claim 1 substantially as herein described with reference
5 to any one of the Examples.

ELKINGTON & FIFE,
Chartered Patent Agents,
High Holborn House, 52/53 High Holborn,
London WC1V 6SH,
Agents for the Applicants.

Printed for Her Majesty's Stationery Office, by the Courier Press, Leamington Spa, 1974.
Published by The Patent Office, 25 Southampton Buildings, London, WC2A 1AY, from
which copies may be obtained.




FIG. 1




FIG. 2